

ALAMBRE NICROM 80-20

| CALIBRE SWG | DIAMETRO | | RESISTENCIA | |
|----------------|-------------|---------------|-------------|------------|
| | MM | PULG MIL | OHMS/MTO | MTO/KG |
| 2 | 5.4 | 0.2575 | 0.0324 | 3.5 |
| 4 | 5.19 | 0.2043 | 0.0515 | 5.7 |
| 5 | 4.26 | 0.1819 | 0.0647 | 7.2 |
| 6 | 4.12 | 0.1622 | 0.082 | 9 |
| 7 | 3.67 | 0.1445 | 0.1033 | 11 |
| 8 | 3.26 | 0.1283 | 0.1302 | 14 |
| 9 | 2.91 | 0.1146 | 0.1643 | 18 |
| 10 | 2.59 | 0.102 | 0.2073 | 23 |
| 11 | 2.3 | 0.0906 | 0.2614 | 29 |
| 12 | 2.03 | 0.0807 | 0.328 | 36 |
| 13 | 1.83 | 0.072 | 0.417 | 46 |
| 14 | 1.63 | 0.0642 | 0.525 | 58 |
| 15 | 1.45 | 0.0571 | 0.659 | 73 |
| 16 | 1.29 | 0.0508 | 0.833 | 92 |
| 17 | 1.15 | 0.0453 | 1.049 | 116 |
| 18 | 1.02 | 0.0402 | 1.325 | 146 |
| 19 | 0.91 | 0.0358 | 1.669 | 185 |
| 20 | 0.81 | 0.0319 | 2.099 | 232 |
| 21 | 0.72 | 0.0283 | 2.64 | 293 |
| 22 | 0.64 | 0.0252 | 3.346 | 370 |
| 23 | 0.57 | 0.0224 | 4.198 | 466 |
| 24 | 0.51 | 0.0201 | 5.314 | 589 |
| 25 | 0.46 | 0.0181 | 6.724 | 742 |
| 26 | 0.404 | 0.0159 | 8.5 | 941 |
| 27 | 0.361 | 0.0142 | 10.7 | 1179 |
| 28 | 0.32 | 0.0126 | 13.5 | 1497 |
| 29 | 0.287 | 0.0113 | 16.8 | 1863 |
| 30 | 0.254 | 0.01 | 21.1 | 2330 |
| 34 | 0.16 | 0.0063 | 54.2 | 5995 |
| 36 | 0.127 | 0.005 | 86 | 9515 |
| 38 | 0.102 | 0.004 | 134.4 | 14814 |
| 40 | 0.079 | 0.0031 | 223.8 | 24656 |
| 42 | 0.064 | 0.0025 | 344.1 | 37915 |

INFORMACION TECNICA ALAMBRES

NiCrome 80% - 20 %
(valores tomados a
Temperatura de 20°C)